



DANISH
TECHNOLOGICAL
INSTITUTE

Test Report no. A 455279-4

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric Hallingdal	
Design:	Received: 07-11-2011 Completed: 14-11-2011
Fibre content: 70 % New wool, 30 % viscose (Manufacturer's information)	Sample no.: 455279-4
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Determination of the slippage resistance of yarns at a seam in woven fabrics - Fixed load method ISO/FDIS 13936-2:2004 Performed on: Standard seam Load: 180 N	Average of 5 determinations Seam parallel to warp: 4,5 mm seam opening Seam parallel to weft: 4 mm seam opening

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

14 November 2011, Danish Technological Institute, Textile

Charlotte Fischer

Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

Lea Larsen

Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader