



Page : 1 of 1

Revision nr. : 3

Approved by : BV

Test report Seam Slippage NS-EN 13936-2

Client SAHCO GmbH KREUZBURGER STRASSE 17-19 DE-9047 1 NÜRNBERG GERMANY		Product VTZ 2543-3 Zolla	
Client's reference Sarah Kemmerer		Product specification - tested object	
R-no. R16491			
Date 27.03.2019	Date of receipt, tested object 15.03.2019	Test completed date 26.03.2019	Rev. no. / Rev. date 0/

MANUFACTURER:

COMPOSITION:

Determination of the seam tension properties according to NS EN ISO 13936-2.
Five specimens are taken in each direction.
The test specimens are folded and sewn. The specimens are set in a tensile strength tester.
A force of 180 N is applied. The gap is measured in mm to nearest 0,5 mm.

	SEAM PARALLELL TO WEFT:	SEAM PARALLELL TO WARP:
Sample no.1:	4,5 mm	1,0 mm
Sample no.2:	4,5 mm	1,0 mm
Sample no.3:	5,0 mm	1,0 mm
Sample no.4:	5,0 mm	1,0 mm
Sample no.5:	5,0 mm	1,0 mm
Average seam gap:	5,0 mm	1,0 mm

Comments:

Deviations from test standards:

Bård Vestre
Manager