

Page : 1 of 1

Revision nr. : 3

Approved by: BV

## Test report Seam Slippage NS-EN 13936-2

Client SAHCO GmbH KREUZBURGER STRASSE 17-19 DE-9047 1 NÜRNBERG Tyskland		Product  Moire  Product specification - tested object						
				Client's reference		R-no.		
				Sarah Kemmerer		R16520		
				Date	Date of receipt, tested object	Test completed date	Rev. no. / Rev. date	
11.04.2019	08.04.2019	11.04.2019	0/					

MANUFACTURER:

COMPOSITION:

Determination of the seam tension properties according to NS EN ISO 13936-2.

Five specimens are taken in each direction.

The test specimens are folded and sewn. The specimens are set in a tensile strength tester.

A force of 180 N is applied. The gap is measured in mm to nearest 0,5 mm.

	SEAM PARALLELL TO WEFT:	SEAM PARALLELL TO WARP:
Sample no.1:	2,0 mm	3,0 mm
Sample no.2:	2,0 mm	2,5 mm
Sample no.3:	2,0 mm	2,5 mm
Sample no.4:	2,0 mm	2,5 mm
Sample no.5:	2,0 mm	3,5 mm
Average seam gap:	2,0 mm	2,5 mm

Comments:	
Deviations from test standards:	

Bård Vestre