



**Feabrik bv
Mevr. Renee Merckx
Minosstraat 20
5048 CK TILBURG
Nederland**

Your notice of
07-01-2014

Your reference

Date
11-07-2019

Analysis Report 14.00065.04

Required tests :

ISO 12945-2 (2000)


Determination of the resistance to pilling - Martindale

Identification number	Information given by the client	Date of receipt
T1319013	Triangle Chalk	09-12-2013



Joceleyne Coreelman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T1319013r - Triangle Chalk

Determination of the resistance to pilling - Martindale

Date of ending the test 09-01-2014
 Standard used ISO 12945-2 (2000)

Deviation from the standard -
 Conditioning 20°C, relative humidity 65%
 Apparatus Martindale Wear and Abrasion Tester
 Pressure on test specimen 6,5 cN/cm²
 Abradant Crossbred worsted spun, plain woven fabric
 Number of test specimens 3
 Number of assessors 2

	Assessment at ... number of cycles			
	500	1000	2000	5000
#1	4-5	4-5	4-5	4-5
#2	4-5	4-5	4-5	4-5
#3	4-5	4-5	4-5	4-5

The final assessment is based on
 Annex 1

Pilling
 Pilling samples in attachment



Sample history

T1319013r **Triangle Chalk**
Sample reused from order A1305784