



Feabrik bv
Mevr. Fatima El Madidi
Minosstraat 20
5048 CK TILBURG
Nederland

Your notice of
04-02-2019

Your reference

Date
21-05-2019

Analysis Report 19.00642.06

Required tests :


ISO 12945-2 (2000)

Determination of the resistance to pilling - Martindale

| Identification number | Information given by the client | Date of receipt |
|-----------------------|---------------------------------|-----------------|
| T1902535 | 13020 Plecto Cosmos Orange 0784 | 04-02-2019 |

Lies Alboort
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T1902535 - 13020 Plecto Cosmos Orange 0784

Determination of the resistance to pilling - Martindale

Date of ending the test 14-02-2019
 Standard used ISO 12945-2 (2000)
 Product standard EN 14465 (2003) + A1 (2006)

Deviation from the standard -
 Conditioning 20°C, relative humidity 65%
 Apparatus Martindale Wear and Abrasion Tester
 Pressure on test specimen 6,5 cN/cm²
 Abradant Crossbred worsted spun, plain woven fabric
 Number of test specimens 3
 Number of assessors 2

| | Assessment at ... number of cycles | | | |
|----|------------------------------------|------|------|------|
| | 500 | 1000 | 2000 | 5000 |
| #1 | 5 | 4-5 | 4 | 3-4 |
| #2 | 5 | 4-5 | 4 | 3-4 |
| #3 | 5 | 4-5 | 4 | 3-4 |

The final assessment is based on Pilling