



TEST REPORT

Client: Kvadrat AS
Lundebergsvej 10
8400 EBELTOFT
Denmark

Entry No: 70893-04 (amended)

Date received: 07/07/2015

Client's Description: Sample of fabric: REFLEX

Test Required: Pilling

Conditioning: In accordance with BS EN ISO 139 : 2005 for a minimum of 24 hours at 65+/-4%, Relative Humidity, 20+/-2°C

Date Tests Completed: 07/08/2015

Pilling: BS EN ISO 12945-2: 2000 Load 415g

	<u>Rating</u>
After 500 rubs	4
After 1,000 rubs	4
After 2,000 rubs	3-4
After 5,000 rubs	3-4

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Vivienne Brockbank
Senior Technician
Date of original 26 August 2015
Date of amendment 05 October 2015

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
 - ❖ Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
 - ❖ Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104