



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 492355-6

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltøft	
Test material: Upholstery fabric Basel 121/181	
Design:	Received: 04-09-2011 Completed: 17-09-2012
Fibre content: 90 % new wool, 10 % nylon (Manufacturer's information)	Sample no.: 492355-6
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results																					
Abrasion resistance - Martindale EN ISO 12947-2:1998 Mass: 795 g Nominal pressure: 12 kPa Breakdown point: Two broken threads	Individual results: > 50 000 - > 50 000 - > 50 000 rubs																					
Determination of fabric propensity to surface fuzzing and to pilling EN ISO 12945-2:2000 Modified Martindale method 1-5 scale, 5 best rating Number of test specimens: 3 Number of observers: 2 Pre-treatment: none Abradant: Wool abradant fabric Loading mass: 415 g	<table border="1"> <thead> <tr> <th><u>Assessment stage</u></th> <th><u>Number of rubs</u></th> <th><u>Pilling grade</u></th> </tr> </thead> <tbody> <tr> <td>1</td> <td>500</td> <td>4</td> </tr> <tr> <td>2</td> <td>1000</td> <td>4</td> </tr> <tr> <td>3</td> <td>2000</td> <td>4</td> </tr> <tr> <td>4</td> <td>5000</td> <td>4</td> </tr> <tr> <td colspan="2">Final grade</td> <td>4</td> </tr> <tr> <td colspan="3">The final grading at 2000 rubs relates to fuzzing</td> </tr> </tbody> </table>	<u>Assessment stage</u>	<u>Number of rubs</u>	<u>Pilling grade</u>	1	500	4	2	1000	4	3	2000	4	4	5000	4	Final grade		4	The final grading at 2000 rubs relates to fuzzing		
<u>Assessment stage</u>	<u>Number of rubs</u>	<u>Pilling grade</u>																				
1	500	4																				
2	1000	4																				
3	2000	4																				
4	5000	4																				
Final grade		4																				
The final grading at 2000 rubs relates to fuzzing																						

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

17 September 2012, Danish Technological Institute, Textile

Charlotte Fischer

Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

Lea Larsen

Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 492355-4

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric Basel 123/183	
Design:	Received: 04-09-2011 Completed: 17-09-2012
Fibre content: 90 % new wool, 10 % nylon (Manufacturer's information)	Sample no.: 492355-4
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results																					
Abrasion resistance - Martindale EN ISO 12947-2:1998 Mass: 795 g Nominal pressure: 12 kPa Breakdown point: Two broken threads	Individual results: > 50 000 - > 50 000 - > 50 000 rubs																					
Determination of fabric propensity to surface fuzzing and to pilling EN ISO 12945-2:2000 Modified Martindale method 1-5 scale, 5 best rating Number of test specimens: 3 Number of observers: 2 Pre-treatment: none Abradant: Wool abradant fabric Loading mass: 415 g	<table border="1"> <thead> <tr> <th>Assessment stage</th> <th>Number of rubs</th> <th>Pilling grade</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>500</td> <td>4</td> </tr> <tr> <td>2</td> <td>1000</td> <td>4</td> </tr> <tr> <td>3</td> <td>2000</td> <td>4</td> </tr> <tr> <td>4</td> <td>5000</td> <td>4</td> </tr> <tr> <td colspan="2">Final grade</td> <td>4</td> </tr> <tr> <td colspan="3">The final grading at 2000 rubs relates to fuzzing</td> </tr> </tbody> </table>	Assessment stage	Number of rubs	Pilling grade	1	500	4	2	1000	4	3	2000	4	4	5000	4	Final grade		4	The final grading at 2000 rubs relates to fuzzing		
Assessment stage	Number of rubs	Pilling grade																				
1	500	4																				
2	1000	4																				
3	2000	4																				
4	5000	4																				
Final grade		4																				
The final grading at 2000 rubs relates to fuzzing																						

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

17 September 2012, Danish Technological Institute, Textile

Charlotte Fischer

Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

Lea Larsen

Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 492355-5

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric Basel 126/186	
Design:	Received: 04-09-2011 Completed: 17-09-2012
Fibre content: 90 % new wool, 10 % nylon (Manufacturer's information)	Sample no.: 492355-5
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results																		
Abrasion resistance - Martindale EN ISO 12947-2:1998 Mass: 795 g Nominal pressure: 12 kPa Breakdown point: Two broken threads	Individual results: > 50 000 - > 50 000 - > 50 000 rubs																		
Determination of fabric propensity to surface fuzzing and to pilling EN ISO 12945-2:2000 Modified Martindale method 1-5 scale, 5 best rating Number of test specimens: 3 Number of observers: 2 Pre-treatment: none Abradant: Wool abradant fabric Loading mass: 415 g	<table border="1"> <thead> <tr> <th><u>Assessment stage</u></th> <th><u>Number of rubs</u></th> <th><u>Pilling grade</u></th> </tr> </thead> <tbody> <tr> <td>1</td> <td>500</td> <td>3-4</td> </tr> <tr> <td>2</td> <td>1000</td> <td>3-4</td> </tr> <tr> <td>3</td> <td>2000</td> <td>3-4</td> </tr> <tr> <td>4</td> <td>5000</td> <td>3-4</td> </tr> <tr> <td colspan="2">Final grade</td> <td>3-4</td> </tr> </tbody> </table> The final grading at 2000 rubs relates to fuzzing and pilling	<u>Assessment stage</u>	<u>Number of rubs</u>	<u>Pilling grade</u>	1	500	3-4	2	1000	3-4	3	2000	3-4	4	5000	3-4	Final grade		3-4
<u>Assessment stage</u>	<u>Number of rubs</u>	<u>Pilling grade</u>																	
1	500	3-4																	
2	1000	3-4																	
3	2000	3-4																	
4	5000	3-4																	
Final grade		3-4																	

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

17 September 2012, Danish Technological Institute, Textile

Charlotte Fischer
 Charlotte Fischer
 Ph Direct: +45 72 20 21 35
 E-mail: charlotte.fischer@teknologisk.dk
 Test responsible

Lea Larsen
 Lea Larsen
 Ph Direct: +45 72 20 21 36
 E-mail: lea.larsen@teknologisk.dk
 Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 492355-2

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric Basel 127/187	
Design:	Received: 04-09-2011 Completed: 17-09-2012
Fibre content: 90 % new wool, 10 % nylon (Manufacturer's information)	Sample no.: 492355-2
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results																					
Abrasion resistance - Martindale EN ISO 12947-2:1998 Mass: 795 g Nominal pressure: 12 kPa Breakdown point: Two broken threads	Individual results: > 50 000 - > 50 000 - > 50 000 rubs																					
Determination of fabric propensity to surface fuzzing and to pilling EN ISO 12945-2:2000 Modified Martindale method 1-5 scale, 5 best rating Number of test specimens: 3 Number of observers: 2 Pre-treatment: none Abradant: Wool abradant fabric Loading mass: 415 g	<table border="1"> <thead> <tr> <th>Assessment stage</th> <th>Number of rubs</th> <th>Pilling grade</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>500</td> <td>3-4</td> </tr> <tr> <td>2</td> <td>1000</td> <td>3-4</td> </tr> <tr> <td>3</td> <td>2000</td> <td>3-4</td> </tr> <tr> <td>4</td> <td>5000</td> <td>3-4</td> </tr> <tr> <td colspan="2">Final grade</td> <td>3-4</td> </tr> <tr> <td colspan="3">The final grading at 2000 rubs relates to fuzzing and pilling</td> </tr> </tbody> </table>	Assessment stage	Number of rubs	Pilling grade	1	500	3-4	2	1000	3-4	3	2000	3-4	4	5000	3-4	Final grade		3-4	The final grading at 2000 rubs relates to fuzzing and pilling		
Assessment stage	Number of rubs	Pilling grade																				
1	500	3-4																				
2	1000	3-4																				
3	2000	3-4																				
4	5000	3-4																				
Final grade		3-4																				
The final grading at 2000 rubs relates to fuzzing and pilling																						

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

17 September 2012, Danish Technological Institute, Textile

Charlotte Fischer

Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

Lea Larsen

Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 492355-3

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric Basel 129/189	
Design:	Received: 04-09-2011 Completed: 17-09-2012
Fibre content: 90 % new wool, 10 % nylon (Manufacturer's information)	Sample no.: 492355-3
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results																		
Abrasion resistance - Martindale EN ISO 12947-2:1998 Mass: 795 g Nominal pressure: 12 kPa Breakdown point: Two broken threads	Individual results: > 50 000 - > 50 000 - > 50 000 rubs																		
Determination of fabric propensity to surface fuzzing and to pilling EN ISO 12945-2:2000 Modified Martindale method 1-5 scale, 5 best rating Number of test specimens: 3 Number of observers: 2 Pre-treatment: none Abradant: Wool abradant fabric Loading mass: 415 g	<table border="1"> <thead> <tr> <th>Assessment stage</th> <th>Number of rubs</th> <th>Pilling grade</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>500</td> <td>4</td> </tr> <tr> <td>2</td> <td>1000</td> <td>4</td> </tr> <tr> <td>3</td> <td>2000</td> <td>4</td> </tr> <tr> <td>4</td> <td>5000</td> <td>4</td> </tr> <tr> <td>Final grade</td> <td></td> <td>4</td> </tr> </tbody> </table> The final grading at 2000 rubs relates to fuzzing	Assessment stage	Number of rubs	Pilling grade	1	500	4	2	1000	4	3	2000	4	4	5000	4	Final grade		4
Assessment stage	Number of rubs	Pilling grade																	
1	500	4																	
2	1000	4																	
3	2000	4																	
4	5000	4																	
Final grade		4																	

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

17 September 2012, Danish Technological Institute, Textile

Charlotte Fischer

Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

Lea Larsen

Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader