



Doc. no. : SK-71

Page : 1 of 1

Revision no. : 8

Approved by : BV



Test report Textile Pilling NS-EN ISO 12945-2 :2000

Client SAHCO GmbH KREUZBURGER STRASSE 17-19 DE-9047 1 NÜRNBERG GERMANY		Product Zero / 60073	
Client's reference Sarah Kemmerer		Product specification - tested object	
Date 21.03.2019		R-no. R16496	
Date of receipt, tested object 15.03.2019	Test completed date 20.03.2019	Rev. no. / Rev. date 0/	

Manufacturer:

Composition: 65% Co, 20% AC, 15% PE

Loading Mass : 415 g Type felt: Woven

The samples are conditioned at 20 degrees C and 65 % relative humidity for 18 hours

Numerical assessment of pilling is done on a Martindale abrasion tester according to NS-EN ISO 12945-2. The samples are given a multi-directional movement and are rubbed against fabric of 100% wool (SM 25). 3 samples are used and they are examined at 500, 1000, 2000 and 5000 rubs. The average on each stage is reported as the pilling grade.

The samples are examined on a scale from 1-5 where 5 is best. Examined by 1 person.

Results:	500 Cycles: 4-5
	1000 Cycles: 4-5
	2000 Cycles: 4-5
	5000 Cycles: 4-5

Comments:

Deviations from test standards:

Bård Vestre
Manager