## **Textiles F.R. Limited**

Flame Retardancy Finishers & Consultants



Unit 4B, (30) Wharfedale Road Euroway Trading Estate Bradford West Yorkshire BD4 6SG

Tel: 01274 651230 Fax: 01274 651305

E-mail: sales@textilesfr.co.uk Web site: www.textilesfr.co.uk



## Test Report & Certificate

## UKAS TESTING LABORATORY No.1413

British Standard Flammability Test Document: 20382

Page 1 of 1

BS5852:Part 1:1979:Source 1

Match Equivalent

Customer Account: SAH003 SAHCO HESSLEIN GMBH & CO KG KREUZBURGER ST 17-19 D-90471 NURNBERG GERMANY

Order Details : 240767 TFR Order No Customer Order : 2018 JHG
Order Date : 18/12/2017

Fabric Description : 2768-01 SEQUENCE Fabric Composition :

Sample Conditioning

: Test specimens were maintained for at least 72 hours at indoor ambient temperature & humidity prior to introduction to the conditioning room for 16 hours with an environment of 20°C +/- 5°C and Relative Humidity 50% +/- 20% -/- 2

Test Enclosure Conditions

Relative Humidity 49 % : Temperature 24 'C

Cleansing Procedure

: 30 minute water soak (BS5651:1989:Clause 3) : As amended by the Furniture & Furnishings Regulations 1988 : Fabric treated with a flame retardant backcoating chemical

Quantity (metres)

Filling materials used in composite: Non-combustion modified foam (approximate density 22Kg/cubic metre)

Test Procedure:
The test sample of dimension 800mm (warp) x 650mm (weft) was exposed to a match equivalent butane flame (placed between the test assembly seat & back for 20 seconds. Any combustion activity was noted. Flame extinction was recorded from the time the ignition source was removed.

The following results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials when in use.

OBSERVATIONS		Rep1	Rep2
Unsafe escalating combustion	:	No	No
Test assembly consumed	:	No	No
Smoulders to extremities	:	No	No
Smoulders through thickness	:	No	No
Smoulders more than one hour	:	No	No
Progressive Smouldering	:	No	No
Flames for >120 seconds	:	No	No
Flames to extremities	:	No	No
Flames through thickness	:	No	No
Melting	:	No	No
Dripping	:	No	No
Charring	:	Yes	Yes

MEASUREMENTS Repl Rep2 Sample ignition (sec): 11 Flame extinction (sec): 1 Cover split 0 (sec):

Comments:

COMPLIANCE REQUIREMENTS: No escalating smouldering or flaming combustion behaviour so that it is unsafe to continue the test and forcible extinction is required. The specimen should not essentially be consumed or smoulder or flame to its side extremities or to its full depth. All flaming should cease within 120 seconds after removal of the burner tube. No evidence of progressive smouldering. No isolated floor fires originating from specimen debris.

Specimen complied with the requirements for BS5852:Part 1:1979:Source 1

Conducted by : Mr.R. BERRY

Laboratory Technician Authorised by: Miss K. BUTTON

Office Manager

Date 05/01/2018

Date 05/01/2018