

BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

19 September 2011

Our Ref: 27/02366/09/11

Your Ref:

Page 1 of 3

Client:

Kvadrat A/S Lundbergsvej 10 8400 Ebeltoft Denmark

Job Title:

Fire Test on One Sample of Fabric

Clients Order Ref:

Date of Receipt:

26 September 2011

Description of Sample:

One sample of fabric, referenced: Time 300/Timeless, 100% Trevira

CS.

Work Requested:

Fire Technology Services were requested to carry out a fire test on

the sample supplied to BS5867 Part 2 Type B.







BTTG Testing & Certification Ltd. Wira House West Park Ring Road Leeds, LS16 6QL England

> Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

19 September 2011

Page 2 of 3

Our Ref: 27/02366/09/11

Your Ref:

Kvadrat A/S

Fire Tests According to BS 5867-2:Type B:2008 Fabrics for curtains, drapes and window blinds - Flammability requirements, Specification

Date of Test: 17/10/11

Procedure

The specimen were tested in accordance with BS EN ISO 15025:Procedure A:2002, as required by BS 5867:Type B.

Sets of specimens were tested before and after the water soaking procedure described in BS EN 1021-1:Annexe D:2006.

The specimens were tested using a flame application time of 15 seconds.

Requirements

BS 5867 states that:-

'No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of the sample. If any part of any hole or any part of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens shall be tested. If all six new specimens comply with the above requirements, the fabric shall be deemed to conform to the requirements for type 'B' of this British Standard.'

Results

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Before Water Soaking

Number of specimens where the hole reached any edge	-	0
Number of specimens where the flame reached any edge)	0
Number of specimens where there was flaming debris droplets	5000 6	0

After Water Soaking

Number of specimens where the hole reached any edge	-	0
Number of specimens where the flame reached any edge		0
Number of specimens where there was flaming debris droplets		0







BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

Page 3 of 3

19 September 2011

Our Ref: 27/02366/09/11

Your Ref:

Kvadrat A/S

Comments

The results indicate the sample meets the Type B performance requirements.

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

Reported by: B Marsden (Mrs), Fire Technician

Countersigned by: P Doherty, Operational Head

Enquiries concerning this report should be addressed to Sestomer Services.



