

Received:02/05/2020 Completed:02/10/2020 Letter: X JR P.O.#: Test Report #: 3-37088-0-

Client's Identification Style: Maya. Composition: 100% Trevira CS. Weight: 100 g/m². Thickness: 0-1 mm. Product End Use: Curtain Fabric.

Tested For: Lone Henriksen **Key Test: NFPA 701-2019 TM#1** 295
 Kvadrat A/S
 Lundbergsvej 10 **Tel: 011 45 89 53 18 66** **Ext:**
 8400 Ebeltoft Denmark **Fax: 011 45 89 53 18 00**

LE:2019 V:01/19 PC: 0.5H DL/jd

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2019 Edition - Test Method #1

PRODUCT CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially; After 3 dry cleanings; After 5 launderings @ 160°F

RESULTS:

Specimen #	Afterflame* (seconds)	Flamming Drip/Debris (seconds)	Weight Loss (percent)
1	0	0	34.3
2	0	0	40.0
3	0	0	28.6
4	0	0	26.5
5	0	0	28.6
6	0	0	20.0
7	0	0	31.4
8	0	0	31.4
9	0	0	32.4
10	0	0	26.5
	Mean:	0	Mean: 30.0

STATISTICAL VALUES: SD = 5.3 3 SD = 16.0 Mean + 3 SD = 46.0

ABBREVIATIONS USED: SD = Standard deviation. NT = Not tested.

APPROXIMATE WEIGHT OF MATERIAL (as measured by SGS): 114 g/m²

PRECONDITIONING: 0.5 hr @ 220°F (Standard)
 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTOR: g/m² ÷ 28.35 x .835 = oz/yd²

NOTE:

1. All specimens prepared in the length direction.
2. See addendum for individual specimen weights.

Received: 02/05/2020	Completed: 02/10/2020	Letter: X	JR	P.O.#:	Test Report #:	3-37088-0-
Client's Identification	Style: Maya. Composition: 100% Trevira CS. Weight: 100 g/m ² . Thickness: 0-1 mm. Product End Use: Curtain Fabric.					
Tested For: Lone Henriksen	Key Test: NFPA 701-2019 TM#1				295	
Kvadrat A/S Lundbergsvej 10 8400 Ebeltoft Denmark			Tel: 011 45 89 53 18 66		Ext:	
			Fax: 011 45 89 53 18 00			

REMARKS:

- Flames did not project above the top of the specimen.
- Flames projected above the top of the specimen; Specimen #'s _____
- Other: _____

FAILURE CRITERIA: As cited by NFPA 701 - 2019 Edition Test Method #1

Afterflame	Flaming Drip/Debris (Mean)	Weight Loss (percent)	
		Mean	Individual Specimen
*	Exceeds 2 seconds	Exceeds 40%	Exceeds Mean + 3 SD

CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFPA 701 - 2019 Edition Test Method #1, the item tested:


- Passes; Fails; Requires testing of 10 additional specimens
i.e. only one individual specimen failure was noted

* Afterflame is required to be recorded; however, the NFPA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames could be cause for rejection by local fire authorities performing "match" field tests.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

 AUTHORIZED SIGNATURE

SGS
 /mg AB



Bobby Brown

FEB 18 2020