

Received:06/20/2019	Completed:06/24/2019	Letter: M	BG	P.O.#:	Test Report #: I-11168-0-
---------------------	----------------------	-----------	----	--------	---------------------------

Client's Identification	Item Number: 13170121. Description: Parkland 121 by Kvadrat. Batch Number: GA23082-0204.
-------------------------	--

Tested For: Lone Henriksen Kvadrat A/S Lundbergsvej 10 8400 Ebeltøft Denmark	Key Test: CA TB 117-2013 (Section 1-Cover Fabric) Tel: 011 45 89 53 18 66 Fax: 011 45 89 53 18 00	275 Ext:
--	---	--------------------

Specifier: IKEA/CA LE: 2014; V 10/16 NTR 9/16 PC: 24H SM/mg

TEST PERFORMED: California Technical Bulletin 117-2013 - Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture (June 2013 Version) [LE 2013; V 1/19] --

Section 1, Cover Fabric Test (Upholstery cover material is the outermost layer of fabric or related material used to enclose the main support system or upholstery materials, or both, used in the furniture item.) --

As required by IOS-PRF-0047 and IOS-PRF-0048

IGNITION SOURCE: Cigarette

COMPLIANCE COMPONENT IDENTIFICATION:

Material Producer: INSBC

Material Identification: Parkland 121 by Kvadrat

Identification Code: INSBC

Material Batch Number or Equivalent: GA23082-0204

How and Where Sample Was Taken: INSBC

ABBREVIATION WHICH MAY BE USED: INSBC = Information not supplied by client.

Received:06/20/2019	Completed:06/24/2019	Letter: M	BG	P.O.#:	Test Report #:	I-11168-0-
Client's Identification	Item Number: 13170121. Description: Parkland 121 by Kvadrat. Batch Number: GA23082-0204.					
Tested For: Lone Henriksen Kvadrat A/S Lundbergsvej 10 8400 Ebeltoft Denmark			Key Test: CA TB 117-2013 (Section 1-Cover Fabric) Tel: 011 45 89 53 18 66 Fax: 011 45 89 53 18 00			275 Ext:

SPECIMEN TEST COMPOSITE:

Upholstery Cover Material: As described in "Client's Identification".

Standard Substrate Material: Non FR polyurethane foam, density 1.8 ± 0.05 lb/ft³

BRIEF DESCRIPTION OF TEST: Miniature cushions are prepared using the clients cover fabric over the standard filling material. The vertical or back cushions measure 8" x 8" x 2". The horizontal or seat cushions measure 8" x 5" x 2".

A lighted cigarette is placed in the crevice formed by the vertical cushion and the horizontal cushion.

The test is terminated at 45 minutes if smoldering is no longer observed.

Test measurements and observations are recorded.

PASS/FAIL/REPEAT CRITERIA: A material is considered to pass or fail based on the following criteria:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a) The mock-up test specimen continues to smolder after the 45 minute test duration;
 - b) A vertical char length (measured as specified in step 11.9 of ASTM E1353-08ae1) of more than 1.8 inches (45 mm) develops on the cover fabric.
 - c) The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their entire length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

Received: 06/20/2019	Completed: 06/24/2019	Letter: M	BG	P.O.#:	Test Report #: I-11168-0-
----------------------	-----------------------	-----------	----	--------	---------------------------

Client's Identification

Item Number: 13170121. Description: Parkland 121 by Kvadrat. Batch Number: GA23082-0204.

Tested For: Lone Henriksen

Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft Denmark

Key Test: CA TB 117-2013 (Section 1-Cover Fabric) 275

Tel: 011 45 89 53 18 66 Ext:
Fax: 011 45 89 53 18 00

RESULTS:

	Specimen #	Char Length (inches)	SE (yes/no)	SB45 (yes/no)	TOF (yes/no)
Initial:	1	0.4	No	No	No
	2	0.4	No	No	No
	3	0.4	No	No	No
Replacement: (If needed)	1				
	2				
	3				
Repeat Tests: (If needed)	1				
	2				
	3				

EXPLANATION:

Initial: These are the first 3 cigarettes where the results could be sufficient to draw a test conclusion.

Replacement: If any of the initial cigarettes self-extinguish before burning their complete length, a new test is conducted with a fresh cigarette.

Repeat Test: Depending on the initial or replacement results, repeat tests might be required to draw a conclusion.

CODES USED:

SE = Self-extinguished, see Page 4 discussion
SB45 = Smolder beyond 45 minutes
TOF = Transitions to open flaming
MNR = Measurement not recorded as smoldering exceeded 45 minutes or specimen transitioned to open flames
EC = Escalating smoldering combustion: Extinguished by technician at:
(mm:ss) _____ : _____ due to unsafe conditions.

CONCLUSION:

The above results reported for the initial and / or replacement cigarettes are sufficient to indicate:

☒ Passing; ☐ Failure; ☐ Repeat test on 3 additional specimens

The results after conducting the repeat tests indicate:

☐ Passing; ☐ Failure



GOVMARK

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
email: govmark.accounting@sgs.com

Page 4

Received: 06/20/2019	Completed: 06/24/2019	Letter: M	BG	P.O.#:	Test Report #: I-11168-0-
Client's Identification	Item Number: 13170121. Description: Parkland 121 by Kvadrat. Batch Number: GA23082-0204.				
Tested For: Lone Henriksen Kvadrat A/S Lundbergsvej 10 8400 Ebeltøft Denmark			Key Test: CA TB 117-2013 (Section 1-Cover Fabric) 275 Tel: 011 45 89 53 18 66 Ext: Fax: 011 45 89 53 18 00		

REMARKS: None.

DISCUSSION: The current version of California Technical Bulletin 117-2013 has no provision to recognize cigarettes that self-extinguish prior to burning their entire length. However, ASTM E1353 does recognize this phenomenon.

The SGS Govmark report evaluates replacement cigarettes as follows:

If a cigarette self-extinguishes (SE) before burning its entire length, a new cigarette is placed into the test. If the new (replacement) cigarette self-extinguishes or burns its entire length, the result for that specimen will then be evaluated as if the cigarette burned its entire length when assigning the "Passing/Failure" conclusion.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Phyllis Pettit

JUN 26 2019

AUTHORIZED SIGNATURE

SGS GOVMARK

/jab

/pm

(Page 4 of 4)

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from Govmark.