

**Feabrik bv  
Mevr. Renee Merckx  
Minosstraat 20  
5048 CK TILBURG  
Nederland**

**Your notice of**  
07-01-2014

**Your reference**

**Date**  
11-07-2019

## Analysis Report 14.00065.02

Required tests :

**ISO 105-X12 (2001)**

**Determination of the colour fastness to rubbing**


**EN ISO 105-B02 (1999) + Am  
(2002)**

**Determination of the colour fastness to light**

Identification number	Information given by the client	Date of receipt
T1319013	Triangle Chalk	09-12-2013

Joceleyne Coreelman  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T1319013r - Triangle Chalk**

**Determination of the colour fastness to rubbing**

Date of ending the test 09-01-2014  
 Standard used ISO 105-X12 (2001)

Deviation from the standard -  
 Conditioning 20°C, relative humidity 65%  
 Apparatus Crockmeter  
 Applied finger Ø 16 mm  
 Pressure on test specimen 9 N  
 Number of cycles 10

Assessment of staining according to the grey scales (ISO 105 A03)

**Numerical rating**

	Wales direction	Course direction
Dry	4	4
Wet	4	4



**Reference: T1319013r - Triangle Chalk**

**Determination of the colour fastness to light**

Date of ending the test	21-01-2014
Standard used	EN ISO 105-B02 (1999) + Am (2002)
Deviation from the standard	-
Method	1
Apparatus	Xenotest 220+ Atlas
Exposure	Constant
Irradiance	42 W/m <sup>2</sup> @ 300-400 nm
Black standard temperature	47±3°C
Effective humidity	±40%

Assessment according the blue scale standard

Numerical rating      Blue scale grade 7

Annex 1              Exposed sample in annex



## Sample history

**T1319013r**                      **Triangle Chalk**  
Sample reused from order A1305784