



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

## Test Report no. A 524156-1

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Argo	Received: 22-04-2013 Completed: 15-05-2013
Fibre content: 100% Mohair, cotton base web (Manufacturer's information)	Sample no.: 524156-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	112 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	982 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	132 Colour fastness: 5

**Test Report no. A 524156-1**

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	752 Colour fastness: <span style="float: right;">6-7</span>

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.44 of 2013-01-14.

15 May 2013, Danish Technological Institute, Textile



Charlotte Fischer  
 Ph. Direct: +45 72 20 21 35  
 E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen  
 Ph. Direct: +45 72 20 21 36  
 E-mail: lea.larsen@teknologisk.dk

Co-reader



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

## Test Report no. A 702359-1

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Argo 2	Received: 08-06-2016 Completed: 15-07-2016
Fibre content: 100% mohair, cotton backing (Manufacturer's information)	Sample no.: 702359-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	343 <i>FINAL</i> Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	343A Colour fastness: 5
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	443 Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	633 Colour fastness: 4-5

**Test Report no. A 702359-1**

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	743 Colour fastness: 7

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.46 of 2014-04-26.

15 July 2016, Danish Technological Institute, Textile



Charlotte Fischer  
Ph. Direct: +45 72 20 21 35  
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen  
Ph. Direct: +45 72 20 21 36  
E-mail: lea.larsen@teknologisk.dk

Co-reader