

Investigation report

SAHCO GmbH

Fr. Sarah Kemmerer
Kreuzburger Str. 17-19

DE 90471 Nürnberg

contact	Detlef v. Seyfried
department	Laboratory\Laboratory manager
phone	+49 (0) 5206 / 91 07 -57
fax	+49 (0) 5206 / 91 07 -34
e-mail	detlef.vonSeyfried@delcotex.de
date	23.01.2020

investigation report No. 20/40

order description:	<u>Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2</u>
test samples:	art. Glam
sampling:	by the client
orderer:	see address
date of order:	18.12.2019
receipt of order:	20.12.2019
date of testing:	20.01.2020

Remark

The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).



F-88-022-002

DELCOTEX Delius Techtex GmbH & Co. KG ▶ Vilsendorfer Straße 50 ▶ 33739 Bielefeld | Germany
phone +49 5206 9107-0 ▶ fax +49 5206 9107-60 ▶ info@delcotex.de
Geschäftsführung: Dr. Marc Schmidt, Thomas Stark ▶ Handelsregister Bielefeld HRA 14 483 ▶ USt-IdNr. DE813 56 22 67
p.h.G.: DELCOTEX Verwaltungs GmbH ▶ Amtsgericht Bielefeld HRB 37635 ▶ Geschäftsführer: Thomas Stark, Dr. Marc Schmidt
Commerzbank AG Bielefeld ▶ IBAN DE58 4804 0035 0780 8900 00 ▶ BIC COBADEFFXXX

Investigation report No. 20/40

instructions for performing

method:	<u>Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2</u>
measuring conditions:	
tester	Atlas Xenotest alpha LM
light	xenon arc beam
filtersystem	type 7
sample movement	interchangeable barrel
exposure time	240 h - to note 6

test results

art. Glam

article / colour	Note*
art. Glam col. 001 front side	5-6
art. Glam col. 001 back side	5-6
art. Glam col. 002 front side	5
art. Glam col. 002 back side	5
art. Glam col. 003 front side	5
art. Glam col. 003 back side	5
art. Glam col. 004 front side	5
art. Glam col. 004 back side	5
art. Glam col. 005 front side	6
art. Glam col. 005 back side	6
art. Glam col. 006 front side	5-6
art. Glam col. 006 back side	5-6
art. Glam col. 007 front side	5-6
art. Glam col. 007 back side	5-6
art. Glam col. 008 front side	5-6
art. Glam col. 008 back side	5-6
art. Glam col. 009 front side	5-6
art. Glam col. 009 back side	5-6
art. Glam col. 011 front side	5-6
art. Glam col. 011 back side	5-6

* The results based on using the blue scale. Note 1 = intense colour change. Note 8 = no colour change



i.A. Detlef v. Seyfried

Laboratory/Laboratory manager

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information contained in the signed test report is binding.

Investigation report No. 20/40

Attachment

article:

art. Glam

method:

Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

art. Glam matt 001

art. Glam glänzend 001

art. Glam matt 002

art. Glam glänzend 002

art. Glam matt 003

art. Glam glänzend 003

art. Glam matt 004



art. Glam glänzend 004

art. Glam matt 005

art. Glam glänzend 005

art. Glam matt 006

art. Glam glänzend 006



Investigation report No. 20/40

Attachment

article:

art. Glam

method:

Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

art. Glam matt 007

art. Glam matt 010

art. Glam glänzend 007

art. Glam glänzend 010

art. Glam matt 008

art. Glam glänzend 008

art. Glam matt 009

art. Glam glänzend 009

