



Test Report no. A 1217488/330161-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Curtain fabric	
Design: Zulu	Received: 14-09-2009 Completed: 14-10-2009
Fibre content: 100% Trevira CS (Manufacturer's information)	Ref. no.: 1217488 Sample no.: 330161-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	104 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	134 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	154 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	174 Colour fastness: 7

Test Report no. A 1217488/330161-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	474 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	614 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	654 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	694 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	194 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	234 Colour fastness: 7

Test Report no. A 1217488/330161-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	394 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	434 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	834 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	854 Colour fastness: 7


The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract

14 October 2009, Danish Technological Institute, Textile



Charlotte Fischer
 Ph. Direct: +45 72 20 21 35
 E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Rosa Elisabeth Gerdes
 Ph. Direct: +45 72 20 21 29
 E-mail: rosa.elisabeth.gerdes@teknologisk.dk

Co-reader