



**Test Report no. A 487026-1**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: <del>Upholstery</del> fabric Casa	
Design:	Received: 17-07-2012 Completed: 27-08-2012
Fibre content: 100% Trevira CS (Manufacturer's information)	Sample no.: 487026-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	632 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	652 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	232 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	732 Colour fastness: 7

**Test Report no. A 487026-1**

<b>Test Methods</b>	<b>Results</b>
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	722 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	752 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	252 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	292 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	212 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	132 Colour fastness: 7

## Test Report no. A 487026-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	122 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	952 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	932 Colour fastness: 7

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

27 August 2012, Danish Technological Institute, Textile

Charlotte Fischer  
 Ph. Direct: +45 72 20 21 35  
 E-mail: charlotte.fischer@teknologisk.dk

Test responsible

Jeanette Berner Hansen  
 Ph. Direct: +45 72 20 21 39  
 E-mail: jeanette.berner.hansen@teknologisk.dk

Co-reader