

**Test Report no. A 1217488/137387-1**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Curtain fabric	
Design: Ginger	Received: 11-01-2006 Completed: 13-02-2006
Fibre content: 100% Trevira CS (Manufacturers information)	Ref. no.: 1217488 Sample no.: 137387-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	381 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	181 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	641 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	601 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	681 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	541 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	441 Colour fastness: 6

**Test Report no. A 1217488/137387-1**


<b>Test Methods</b>	<b>Results</b>
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	901 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	221 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	141 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	921 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	981 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	341 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	121 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	201 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	401 Colour fastness: 7


**Test Report no. A 1217488/137387-1**

<b>Test Methods</b>	<b>Results</b>
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	101 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	421 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	941 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	741 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	721 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:1994 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	781 Colour fastness: 6

The test has been performed according to the rear side conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract

14 February 2006, Danish Technological Institute, Textile

  
Charlotte Fischer  
Test responsible

  
Dorte Corvinius  
Co-reader



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

**Test Report no. A 653985-1**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Curtain fabric	
Design: Ginger 2	Received: 17-06-2015 Completed: 07-07-2015
Fibre content: 100% Trevira CS (Manufacturer's information)	Sample no.: 653985-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	292 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	722 Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	972 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	792 Colour fastness: 4-5  <b>IMPROVED</b>

**Test Report no. A 653985-1**

<b>Test Methods</b>	<b>Results</b>
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	922 Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	622 Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	152 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	122 Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	462 Colour fastness: 6

**Test Report no. A 653985-1**

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	172 Colour fastness: 5

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.46 of 2014-04-26.

7 July 2015, Danish Technological Institute, Textile



Charlotte Fischer  
Ph Direct: +45 72 20 21 35  
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Signe Beck  
Ph Direct: +45 72 20 24 46  
E-mail: sbk@teknologisk.dk

Co-reader



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

**Test Report no. A 690452-1**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Curtain fabric	
Design: Ginger 2 792	Received: 18-03-2016 Completed: 26-04-2016
Fibre content: 100% Trevira CS (Manufacturer's information)	Sample no.: 690452-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	Colour fastness: 5

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.46 of 2014-04-26.

26 April 2016, Danish Technological Institute, Textile

*Charlotte Fischer*

Charlotte Fischer  
Ph. Direct: +45 72 20 21 35  
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

*Lea Larsen*

Lea Larsen  
Ph. Direct: +45 72 20 21 36  
E-mail: lea.larsen@teknologisk.dk

Co-reader