

kvadrat

Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft Denmark
T +45 89 53 18 66 F +45 89 53 18 00
www.kvadrat.dk kvadrat@kvadrat.dk

CVR 45998517 Jyske Bank 5073 117977-1

Lightfastness ISO 105-B02

Steelcut Trio 3

Colour	Note
105	5
113	6
124	7
133	6
153	5
176	6-7
195	7
205	6-7
213	6
226	6-7
236	6-7
246	6-7
253	6
266	6-7
276	6-7
283	5-6
336	6-7
376	6-7
383	6
416	6-7
426	6-7
436	6-7
446	6-7
453	6
466	6-7
476	6-7
506	6-7
515	7
526	6-7
533	6
553	5-6
576	6-7

616	6-7
636	6-7
645	7
666	6-7
686	6-7
713	6
716	6-7
746	6-7
756	6-7
776	6-7
796	6-7
806	6-7
865	6
883	5-6
906	6-7
916	6-7
946	6-7
953	6-7
966	6-7
976	6-7
983	6
996	6-7

Test reports

DTI A 1217488/202576	25.05.2007
DTI A 1217488/296214	13.02.2009
DTI A 1217488/404092	12.11.2010
DTI A 427083	19.04.2011
DTI A 499060	19.11.2012
High Street 284811	10.11.2016

Test Report no. A 1217488/202576-1

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Steelcut Trio	Received: 10-04-2007 Completed: 25-05-2007
Fibre content: 90% new wool, 10% nylon (Manufacturer's information)	Ref. no.: 1217488 Sample no.: 202576-1
Care label: (Not given)	Your ref.: Lone Henriksen

 Gregersensvej
 DK-2630 Taastrup
 Tel. +45 72 20 20 00
 Fax +45 72 20 20 19

 info@teknologisk.dk
 www.teknologisk.dk


Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	333 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	553 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	653 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	533 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	453 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	983 Colour fastness: 6


Test Report no. A 1217488/202576-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	413 Colour fastness: 6-7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	933 Colour fastness: 6-7

The test has been performed according to the rear side conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract

25 May 2007, Danish Technological Institute, Textile


Charlotte Fischer
Test responsible


Susanna Bjunö
Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 1217488/296214-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltøft	
Test material: Upholstery fabric	
Design: Steelcut Trio	Received: 14-01-2009 Completed: 13-02-2009
Fibre content: 90% new wool/ 10% nylon (Manufacturer's information)	Ref. no.: 1217488 Sample no.: 296214-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	124 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	144 Colour fastness: 7

The test has been performed according to the rear side conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract

13 February 2009, Danish Technological Institute, Textile

Charlotte Fischer

Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Susanna Bjuno

Susanna Bjuno
Ph. Direct: +45 72 20 23 22
E-mail: susanna.bjuno@teknologisk.dk



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 1217488/404092-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Steelcut Trio	Received: 06-10-2010 Completed: 12-11-2010
Fibre content: 90% new wool, 10% nylon (Manufacturer's information)	Ref. no.: 1217488 Sample no.: 404092-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	235 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	865 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	915 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	195 Colour fastness: 7

Test Report no. A 1217488/404092-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	105 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	245 Colour fastness: 4-5 IMPROVED
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	225 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	415 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	565 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	515 Colour fastness: 7

Test Report no. A 1217488/404092-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	645 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	825 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	815 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	945 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	965 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	665 Colour fastness: 6

Test Report no. A 1217488/404092-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	675 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	745 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	845 Colour fastness: 6

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.23 of 2010-10-28.

12 November 2010, Danish Technological Institute, Textile



Charlotte Fischer
 Ph. Direct: +45 72 20 21 35
 E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Jeanette Berner Hansen
 Ph. Direct: +45 72 20 21 39
 E-mail: jeanette.berner.hansen@teknologisk.dk

Co-reader



DANISH
TECHNOLOGICAL
INSTITUTE

Test Report no. A 427083-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Steelcut Trio	Received: 25-03-2011 Completed: 19-04-2011
Fibre content: 90% new wool, 10% nylon (Manufacturer's information)	Sample no.: 427083-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	205 Colour fastness: 6-7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	465 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	425 Colour fastness: 7

Test Report no. A 427083-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	395 Colour fastness: 7

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

19 April 2011, Danish Technological Institute, Textile



Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 499060-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Steelcut Trio	Received: 17-10-2012 Completed: 19-11-2012
Fibre content: 90% new wool, 10% nylon (Manufacturer's information)	Sample no.: 499060-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	683 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	283 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	753 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	883 Colour fastness: 5-6

Test Report no. A 499060-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	733 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	853 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	953 Colour fastness: 6-7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	353 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	383 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	253 Colour fastness: 6

Test Report no. A 499060-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	153 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	133 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	713 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	113 Colour fastness: 6

Test Report no. A 499060-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	213 Colour fastness: 6

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

19 November 2012, Danish Technological Institute, Textile



Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader

Our Ref: SW/LS/JM

10 November 2016

Report 284811

Page 1 of 3

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Sharon Daniel

DATE RECEIVED	: 2 NOV 2016
QUALITY/REFERENCE	: STEELCUT TRIO
REPUTED FIBRE CONTENT	: 90% WOOL, 10% NYLON
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: 176, 226, 236, 246, 266, 276, 336, 376, 416, 426, 436, 446, 466, 476, 506 : 526, 576, 616, 636, 666, 686, 716, 746, 756, 776, 796, 806, 906, 916, : 946, 966, 976, 996
ORDER NUMBER	: 011116
PERFORMANCE STANDARD	: GENERAL

REQUEST: Colour fastness to light



S. WISEMAN
LABORATORY DIRECTOR



L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86



10 November 2016

Report 284811

Page 2 of 3

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
176	6+
226	6+
236	6+
246	6+
266	6+
276	6+
336	6+
376	6+
416	6+
426	6+

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
436	6+
446	6+
466	6+
476	6+
506	6+
526	6+
476	6+
616	6+
636	6+
666	6+

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
686	6+
716	6+
746	6+
756	6+
776	6+
796	6+
806	6+
906	6+
916	6+
946	6+

10 November 2016

Report 284811

Page 3 of 3

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
966	6+
976	6+
996	6+



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

