

Our Ref: SW/LS/JM

4 July 2018

Report 323727

Page 1 of 3

Wooltex UK Limited Woodland Mill Dale Street Longwood Huddersfield, Yorkshire HD3 4TG

Contact: Laura Franklin

DATE RECEIVED OUALITY/REFERENCE REPUTED FIBRE CONTENT FABRIC DESCRIPTION

COLOUR/DESIGN

ORDER NUMBER


PERFORMANCE STANDARD

25 JUN 2018 ATLAS 100% WOOL **WOVEN**

111, 131, 151, 161, 181, 361, 371, 391, 411, 431, 451, 461, 471, 501, 531, 561, 571, 621, 631, 641, 671, 681, 711, 731, 771, 781, 861, 871, 931, 951, 961, 971, 981.

180621

: GENERAL



REQUEST:

Colour fastness to light



LSheridan

S. WISEMAN LABORATORY DIRECTOR

L. SHERIDAN **LABORATORY MANAGER**

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior





4 July 2018

Report 323727

Page 2 of 3

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
111	6+
131	6+
151	6+
161	6
181	6
361	6+
371	6+
391	6+
411	6
431	6+
451	6
461	6+
471	6+
501	6





4 July 2018

Report 323727

Page 3 of 3

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
531	6+
561	6+
571	6+
621	6+
631	6+
641	6+
671	6+
681	6+
711	6+
731	6+
771	6+
781	6+
861	6+
871	6+
881	6+
911	6+

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

Shade	change

931	6+
951	6+
961	6+
971	6+
981	6+





Our Ref: SW/LS/GL

30 July 2018

Report 325360

Page 1 of 2

Wooltex UK Limited Woodland Mill Dale Street Longwood Huddersfield, Yorkshire HD3 4TG

Contact: Laura Franklin

DATE RECEIVED
QUALITY/REFERENCE
REPUTED FIBRE CONTENT
FABRIC DESCRIPTION
COLOUR/DESIGN
ORDER NUMBER

: 19 JUL 2018 : ALTAS : 100% WOOL : WOVEN : 651/660 : 180716/B

PERFORMANCE STANDARD

: GENERAL



REQUEST:

Colour fastness to light

- Mora

LSheridan

S. WISEMAN LABORATORY DIRECTOR

L. SHERIDAN LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.





30 July 2018

Report 325360

Page 2 of 2

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
651	6
661	6

