

Our Ref: SW/LS/GL/BR

24 May 2017

Report 296402

Page 1 of 2

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Sharon Daniel

| | |
|-----------------------|-----------------------|
| DATE RECEIVED | : 2 MAY 2017 |
| QUALITY/REFERENCE | : MELANGE NAP/ FOREST |
| REPUTED FIBRE CONTENT | : 96% WOOL, 4% NYLON |
| FABRIC DESCRIPTION | : WOVEN |
| COLOUR/DESIGN | : MULTI |
| ORDER NUMBER | : 170426 |
| PERFORMANCE STANDARD | : GENERAL |

REQUEST: Colour fastness to light



S. WISEMAN
LABORATORY DIRECTOR



L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

Report 296402

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

| | Shade change |
|-----|--------------|
| 111 | 6+ |
| 171 | 6+ |
| 191 | 6+ |
| 211 | 6+ |
| 221 | 6+ |
| 241 | 6+ |
| 271 | 6+ |
| 321 | 6+ |
| 351 | 6+ |
| 371 | 6+ |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

| | Shade change |
|-----|--------------|
| 411 | 6+ |
| 441 | 6+ |
| 461 | 6+ |
| 491 | 6+ |
| 521 | 6+ |
| 551 | 6+ |
| 651 | 6+ |
| 691 | 6+ |
| 711 | 6+ |
| 751 | 6+ |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

| | Shade change |
|-----|--------------|
| 771 | 6+ |
| 791 | 6+ |
| 871 | 6+ |
| 911 | 6+ |
| 951 | 6+ |
| 991 | 6+ |