

Our Ref: SW/MG/GL

12 May 2014

Report 236640

Page 1 of 2

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Sharon Daniel

DATE RECEIVED	: 9 MAY 2014
QUALITY/REFERENCE	: RIME
REPUTED FIBRE CONTENT	: 90% WOOL, 10% NYLON
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: VARIOUS
END USE	: UPHOLSTERY
ORDER NUMBER	: 080514
PERFORMANCE STANDARD	: GENERAL

REQUEST: Colour fastness to light



S. WISEMAN
LABORATORY DIRECTOR



M. GRAINGER
SENIOR TECHNOLOGIST

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.



118 Lupton Avenue Leeds LS9 6ED
Tel: 0044 (0) 113 248 8830 Fax: 0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

12 May 2014

Report 236640

Page 2 of 2

COLOUR FASTNESS TO:

BS EN ISO 105:1999 B02 LIGHT grade 5

	Shade change
Ref: 721	5+
Ref: 731	5+
Ref: 741	5+
Ref: 781	5+
Ref: 791	5+
Ref: 911	5+
Ref: 921	5+
Ref: 941	5+
Ref: 111	5+
Ref: 131	5+

BS EN ISO 105:1999 B02 LIGHT grade 5

	Shade change
Ref: 151	5+
Ref: 211	5+
Ref: 231	5+
Ref: 271	5+
Ref: 451	5+
Ref: 471	5+
Ref: 521	5+
Ref: 541	5+
Ref: 551	5+
Ref: 571	5+

BS EN ISO 105:1999 B02 LIGHT grade 5

	Shade change
Ref: 591	5+
Ref: 621	5+
Ref: 641	5+
Ref: 691	5+
Ref: 951	5+
Ref: 981	5+
Ref: 991	5+



TEST REPORT NO:107470

Date:15 October 2015

KVADRAT A/S
LUNDBERGSVEJ
DK 8400 EBELTOFT
DENMARK

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer	Not Specified
Description of article	Rime 911 Cotton/ Malt Piece: 2319201
Retailer style number	Rime 951 Bistro/ Sheepskin Piece 2319301
Retailer Standard Number	Unknown
Order No./ Buyer	250915A
Quality/Fibre Composition	90% Wool 10% Nylon
Date Sample(s) Received:	05 October 2015

Test

Colour Fastness to Light (BS EN ISO 105-B02:2013)

BWS	Rime 911 Cotton/Malt	6+
Rating:	Rime 951 Bistro/Sheepskin	6+

Remarks

Tests as requested by the customer

Signature

For and on behalf of
SGS Leicester Ltd.

End of Report

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only.