

# kvadrat

Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltoft Denmark  
T +45 89 53 18 66 F +45 89 53 18 00  
www.kvadrat.dk kvadrat@kvadrat.dk

CVR 45998517 Jyske Bank 5073 117977-1

**Fastness to light**  
**ISO 105-B02, method 2**

## Hallingdal 65

Colour number	Note
100	7
103	5-6
110	7
113	6
116	7
123	6
126	7
130	7
143	5
153	6
166	7
173	6
180	7
190	7
200	6
220	7
224	5
227	6
270	7
350	7
368	7
370	7
376	6-7
390	7
407	7
420	6
457	6-7
526	6-7
547	7
563	6-7
573	6-7

www.kvadrat.dk

590	7
596	7
600	7
657	6-7
660	6
674	6-7
680	6-7
687	6-7
694	7
702	6-7
723	5-6
733	6
750	6
753	6
754	6
763	6
764	6
773	6
810	6
840	6
850	6
890	7
907	5-6
944	6
960	5
968	6
980	6

**Test Report no. A 1217488/189482-1**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Hallingdal	Received: 23-01-2007 Completed: 25-05-2007
Fibre content: 70% new wool, 30% viskose (Manufacturer's information)	Ref. no.: 1217488 Sample no.: 189482-1
Care label: (Not given)	Your ref.: Lone Henriksen


Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	871 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	863 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	870 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	850 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	830 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	877 Colour fastness: 7

## Test Report no. A 1217488/189482-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	893 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	764 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	773 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	753 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	754 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	743 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	573 Colour fastness: 6-7



## Test Report no. A 1217488/189482-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	694 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	687 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	657 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	674 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	523 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	763 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	702 Colour fastness: 4-5 

## Test Report no. A 1217488/189482-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	593 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	543 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	553 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	563 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	123 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	103 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	200 Colour fastness: 6

**Test Report no. A 1217488/189482-1**

<b>Test Methods</b>	<b>Results</b>
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	220 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	337 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	756 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	100 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	796 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	916 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	906 Colour fastness: 5-6

## Test Report no. A 1217488/189482-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	986 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	701 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	370 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	390 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	190 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	173 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	163 Colour fastness: 5-6

## Test Report no. A 1217488/189482-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	153 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	944 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	967 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	927 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	900 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	975 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	901 Colour fastness: 6



## Test Report no. A 1217488/189482-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	600 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	590 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	490 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	547 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	537 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	457 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	180 Colour fastness: 7

## Test Report no. A 1217488/189482-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	130 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	110 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	270 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	350 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	723 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	733 Colour fastness: 6





## Test Report no. A 1217488/189482-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Xenotest 450	750 Colour fastness: 6

The test has been performed according to the rear side conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract

25 May 2007, Danish Technological Institute, Textile

  
Charlotte Fischer  
Test responsible

  
Susanna Bjunö  
Co-reader

**Laboratory Report**

**Fastness test results**

Huntsman Textile Effects

---

Group company	Sweden	Lab Request No.	6671
Issued by	H. Wallentil	Date	26.06.2007
Customer	Gudbrandsdalens Uldvarefabrik A/S	Code	

---

Tests	XENONLIGHT EUROPE (ISO 105-B02)
-------	---------------------------------

---

Samples	Xenonlight 72 / 168 h Rating blue scale
Hallingdel 702	6-7
<del>Soft 2166</del>	<del>4</del>



Andrea Messer  
Huntsman Textile Effects  
c/o Huntsman Advanced Materials (Switzerland) GmbH  
Klybeckstrasse 200, K-411.5.32, CH-4057 Basel, Switzerland  
[andrea\\_messer@huntsman.com](mailto:andrea_messer@huntsman.com)  
Tel: +41 61 636 30 12



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

**Test Report no. A 445702-1**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Hallingdal	Received: 29-08-2011 Completed: 23-09-2011
Fibre content: 70% new wool, 30% viscose (Manufacturer's information)	Sample no.: 445702-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	960 Colour fastness: 5
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	907 Colour fastness: 5-6

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

23 September 2011, Danish Technological Institute, Textile

*Charlotte Fischer*

Charlotte Fischer  
Direkte (lf): +45 72 20 21 35  
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

*Lea Larsen*

Lea Larsen  
Ph. Direct: +45 72 20 21 36  
E-mail: lea.larsen@teknologisk.dk

Co-reader



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

## Test Report no. A 450819-1

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltøft	
Test material: Upholstery fabric Hallingdal	
Design:	Received: 03-10-2011 Completed: 01-11-2011
Fibre content: 70% New wool, 30% Viscose (Manufacturer's information)	Sample no.: 450819-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	680 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	526 Colour fastness: 6-7

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.41 of 2010-12-23.

1 November 2011, Danish Technological Institute, Textile

Lea Larsen  
Ph. Direct: +45 72 20 21 36  
E-mail: lea.larsen@teknologisk.dk

Test responsible

Jeanette Berner Hansen  
Ph. Direct: +45 72 20 21 39  
E-mail: jeanette.berner.hansen@teknologisk.dk

Co-reader



DANISH  
TECHNOLOGICAL  
INSTITUTE

## Test Report no. A 468703-1

Gregersensvej  
DK-2630 Taastrup  
Tel: +45 72 20 20 00  
Fax: +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Hallingdal 65	Received: 17-02-2012 Completed: 30-03-2012
Fibre content: 71% new wool, 305 viscose (Manufacturer's information)	Sample no.: 468703-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	224 Colour fastness: 5
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	227 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	368 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	376 Colour fastness: 6-7



## Test Report no. A 468703-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	113 Colour fastness: 4  IMPROVED
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	116 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	126 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	143 Colour fastness: 4  IMPROVED
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	407 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	420 Colour fastness: 6

## Test Report no. A 468703-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	596 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	660 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	702 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	810 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	840 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	890 Colour fastness: 7



## Test Report no. A 468703-1

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	968 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	980 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	166 Colour fastness: 7

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

30 March 2012, Danish Technological Institute, Textile

*Charlotte Fischer*

Charlotte Fischer  
 Ph. Direct: +45 72 20 21 35  
 E-mail: charlotte.fischer@teknologisk.dk

Test responsible

*Lea Larsen*

Lea Larsen  
 Ph. Direct: +45 72 20 21 36  
 E-mail: lea.larsen@teknologisk.dk

Co-reader

Firm: GUDBRANDSDALENS ULDVAREFABR AS  
Country: NORWAY  
Date: 26.4.2012  
Process: Light fastness - XENONLIGHT EUROPE (ISO 105-B02)  
Technology: Fade Ometer Ci 3000  
Filtration system: CIRA / SODA LIME  
Material: 100% WO yarn

HALLINGDAL

Sample	Light Exposure 114 hrs Rating blue scale
Nr. 7381-880 (red)	≥6
Nr. 3333-201 (grey) · 113	6
Nr. 7381-205 (grey) / 143	5
Nr. 7381-204 (beige)	5