



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 656758-2

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Curtain fabric	
Design: Mi Casa	Received: 13-07-2015 Completed: 13-08-2015
Fibre content: 100% Trevira CS (Manufacturer's information)	Sample no.: 656758-2
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	761 Colour fastness: 6 NOT VALID
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	731 Colour fastness: 6-7 NOT VALID
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	141 Colour fastness: 7
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	131 Colour fastness: 7

Test Report no. A 656758-2

Test Methods	Results
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	811 Colour fastness: 7
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	111 Colour fastness: 7
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	421 Colour fastness: 7
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	451 Colour fastness: 6 NOT VALID
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	431 Colour fastness: 7

Test Report no. A 656758-2

Test Methods	Results
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	631 Colour fastness: 6
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	691 Colour fastness: 4-5 <i>IMPROVED</i>

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.46 of 2014-04-26.

13 August 2015, Danish Technological Institute, Textile



Charlotte Fischer
 Ph. Direct: +45 72 20 21 35
 E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen
 Ph. Direct: +45 72 20 21 36
 E-mail: lea.larsen@teknologisk.dk

Co-reader



DANISH
TECHNOLOGICAL
INSTITUTE

Test Report no. A 685721-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Curtain fabric	
Design: Mi Casa	Received: 23-02-2016 Completed: 17-03-2016
Fibre content: 100% Trevira CS (Manufacturer's information)	Sample no.: 685721-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	691 Colour fastness: 5-6
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	761 Colour fastness: 5-6
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	731 Colour fastness: 6

Test Report no. A 685721-1

Test Methods	Results
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	451 Colour fastness: 6

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.46 of 2014-04-26.

17 March 2016, Danish Technological Institute, Textile



Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader