

Investigation report

SAHCO GmbH
Fr. Sarah Kemmerer
Kreuzburger Str. 17-19

DE 90471 Nürnberg

contact Alicja Rösler
department Laboratory\Lab-manager
phone +49 (0) 5206/9107 -57
fax +49 (0) 5206/9107 -34
e-mail alicja.roesler@delcotex.de
date 13.01.2021

investigation report No. 20/1344_1

order description: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2
test samples: " Art. Stevia, 100% PES FR" diverse colours
brand name: „Art. ASH/600722“
sampling: by the client
orderer: see address
date of order: 07.04.2020/11.01.2021
receipt of order: 07.04.2020
date of testing: 29.04.2020

Remark: The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 20/1344_1

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:

tester Atlas Xenotest alpha LM
light xenon arc beam
filtersystem type 7
sample movement interchangeable barrel
exposure time 166 h - to note 6

test results

Article: " Art. Stevia, 100% PES FR" diverse colours

Brand name: „Art. ASH/600722“ diverse colours

article / colour	Note*
STEVIA col. 01 Brand name: „Art. ASH/600722 col. 200“	6
STEVIA col. 02 Brand name: „Art. ASH/600722 col. 100“	6
STEVIA col. 4 BEIGE Brand name: „Art. ASH/600722 col. 500“	6
STEVIA col. 07 Brand name: „Art. ASH/600722 col. 260“	6
STEVIA col. 11 Brand name: „Art. ASH/600722 col. 130“	6
STEVIA col. 12 Brand name: „Art. ASH/600722 col. 160“	6
STEVIA col. 13 Brand name: „Art. ASH/600722 col. 180“	6
STEVIA col. 17 Brand name: „Art. ASH/600722 col. 720“	6

Investigation report No. 20/1344_1


test results

article / colour	Note*
STEVIA col. 22 Brand name: „Art. ASH/600722 col. 910“	6
STEVIA col. 30 Brand name: „Art. ASH/600722 col. 680“	6

* The results based on using the blue scale.

Note 1 = intense colour change

Note 8 = no colour change

A handwritten signature in blue ink that reads "Alicja Rösler".

i.A. Alicja Rösler

Laboratory/Lab-manager

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.