

Investigation report

SAHCO GmbH
Fr. Sarah Kemmerer
Kreuzburger Str. 17-19

DE 90471 Nürnberg

contact	Alicja Rösler
department	Laboratory\Lab-manager
phone	+49 (0) 5206/9107 -57
fax	+49 (0) 5206/9107 -34
e-mail	alicja.roesler@delcotex.de
date	08.03.2021

investigation report No. 18-E-457-3

order description:	<u>Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2</u>
test samples:	"Clarita 2792, 100% PES Trevira CS"
sampling:	by the client
orderer:	see address
date of order:	27.07.2018
receipt of order:	30.07.2018/24.08.2018/04.03.2021
date of testing:	18.08.2018

Remark: The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 18-E-457-3

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:

tester Atlas Xenotest alpha LM
light xenon arc beam
filtersystem type 7
sample movement interchangeable barrel
exposure time 170 h - to note 6
test equipment number: PM-Nr. 887001


test results

article / colour	Note*
Clarita 2792-05, 100% PES Trevira CS	›6
Clarita 2792-02, 100% PES Trevira CS	›6
Clarita 2792-03, 100% PES Trevira CS	›6
Clarita 2792-04, 100% PES Trevira CS	›6
Clarita 2792-01, 100% PES Trevira CS	›6

* The results based on using the blue scale.

Note 1 = intense colour change

Note 8 = no colour change



i.A. Alicja Rösler

Laboratory/Lab-manager

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.