

**Test report Martindale Abrasion
NS-EN 12947-2 : 1999**

Client SAHCO Hesslein GmbH & Co. KG KREUZBURGER STRASSE 17-19 9047 1 NÜRNBERG Tyskland		Product BURANA	
Client's reference Sarah Kemmerer		Product specification - tested object ELLIS / 2742	
Date 07.06.2016	Date of receipt, tested object 31.05.2016	Test completed date 03.06.2016	Rev. no. / Rev. date 0/

Manufacturer:

Composition: 70% CV, 30% LI

Pressure : 795 g(12 kPa) Type felt: Woven

The samples are conditioned at 20 degrees C and 65 % relative humidity for 18 hours

Determination of the abrasion resistance of textiles on a Martindale testmachine according to NS-EN 12947-2. Circular specimens of fabric are abraded against a reference fabric.

For woven fabrics the resistance to abrasion is estimated by number when two threads are broken.

For pile fabrics the resistance to abrasion is estimated by the number of cycles when the pile is fully worn off. For nonwovens the resistance to abrasion is estimated by the number when there is a hole of 0.5mm.

The average of four samples gives the results.

<p>Sample no. 1: 28000</p> <p>Sample no. 2: 28000</p> <p>Sample no. 3: 28000</p> <p>Sample no. 4: 28000</p> <p>Average 4 Samples: 28000</p>

Comments:

Deviations from test standards:



Bård Vestre
Manager