

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kinnasand / Kvadrat

Date: 30/04/2021

Fabric details Type: Unix
Colour: 2&12
Order:
Item number 67040001
Manufacturer: Kinnasand / Kvadrat

Specimen Diameter: 100 mm
Thickness: 0.65 mm
Area specific mass: 273 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	585
14.16	588
11.80	590
9.44	592
7.12	591
4.72	594



Airflow Resistance

$R_s = 597$ Pa s/m