

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kinnasand / Kvadrat

Date: 30/04/2021

Fabric details Type: Relax
Colour: 2&12
Order:
Item number 67450001
Manufacturer: Kinnasand / Kvadrat

Specimen Diameter: 100 mm
Thickness: 0.75 mm
Area specific mass: 386 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	1744
14.16	1746
11.80	1748
9.44	1752
7.12	1749
4.72	1768



Airflow Resistance

$R_s = 1769$ Pa s/m