

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Sahco / Kvadrat

Date: 14/04/2021

Fabric details Type: Cabana
Colour: 1
Order: 118543
Item number 600190
Manufacturer: Sahco / Kvadrat

Specimen Diameter: 100 mm
Thickness: 0.47 mm
Area specific mass: 233 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	633
14.16	637
11.80	641
9.44	643
7.12	645
4.72	652



Airflow Resistance

$R_s = 657$ Pa s/m