EN 29053 - Determination of airflow resistance

Direct airflow method - method A

Client	Sahco / Kvadrat	
Date:	10/05/2021	
Fabric details	Type:	Salon
	Colour:	2
	Order:	118543
	Item number	600110
	Manufacturer:	Sahco / Kvadrat
Specimen	Diameter:	100 mm
	Thickness:	0.5 mm
	Area specific mass:	199 g/m^2

uI (mm/s)	*$R_s I$ (Pa s/m)*
16.53	300
14.16	303
11.80	306
9.44	313
7.12	316
4.72	322



Airflow Resistance

R_s = 330 Pa s/m

Test conducted by Kvadrat SoftCells
Poznańska 3, 62-023 Gądki