

kvadrat

Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft Denmark
T +45 89 53 18 66 F +45 89 53 18 00
www.kvadrat.dk kvadrat@kvadrat.dk

CVR 45998517 Jyske Bank 5073 117977-1

Fastness to light
ISO 105-B02, method 2

Waterborn

Colour number	Note
123	6-7
133	5
153	4-5
163	4-5
183	4
193	4
203	7
213	5
223	5-6
233	5
243	6
343	4-5
353	4-5
363	4-5
373	4-5
383	4
443	7
453	6
463	6
523	5
543	4
583	4-5
603	6
653	5
663	6-7
673	5
693	4
723	7
743	5
753	5-6
773	5

www.kvadrat.dk

783	4
793	4
853	4-5
883	4
923	5
933	5
953	5-6
973	5

Test reports

DTI, A 1217488/404782-1, dated 12. November 2010
DTI, A 1217488/410591-1, dated 21. December 2010
DTI, A /412761-1, dated 14. January 2011
DTI, A 415493-1, dated 10. February 2011
DTI, A42086-1, dated 7. March 2011

Ebeltoft, March 2011 LH/lh



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 1217488/404782-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Waterborn	Received: 08-10-2010 Completed: 12-11-2010
Fibre content: 85% Polyester, 15% Polyurethane (Manufacturer's information)	Ref. no.: 1217488 Sample no.: 404782-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	133 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	203 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	183 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	163 Colour fastness: 4-5

Test Report no. A 1217488/404782-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	153 Colour fastness: 4-5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	603 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	543 Colour fastness: 3-4 IMPROVED
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	563 Colour fastness: 3-4 DISCONTINUED
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	523 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	883 Colour fastness: 4

Test Report no. A 1217488/404782-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	853 Colour fastness: 4-5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	793 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	783 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	773 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	753 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	743 Colour fastness: 5

Test Report no. A 1217488/404782-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	723 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	693 Colour fastness: 4 IMPROVED
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	673 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	663 Colour fastness: 6-7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	653 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	463 Colour fastness: 6

Test Report no. A 1217488/404782-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	453 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	443 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	393 Colour fastness: 4 DISCONTINUED
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	243 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	233 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	223 Colour fastness: 5-6

Test Report no. A 1217488/404782-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	213 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	973 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	953 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	933 Colour fastness: 5

Test Report no. A 1217488/404782-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	923 Colour fastness: 5

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.23 of 2010-10-28.

12 November 2010, Danish Technological Institute, Textile



Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Jeanette Berner Hansen
Ph. Direct: +45 72 20 21 39
E-mail: jeanette.berner.hansen@teknologisk.dk

Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 1217488/410591-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Waterborn	Received: 22-11-2010 Completed: 21-12-2010
Fibre content: 85% polyester/ 15% polyurethane (Manufacturer's information)	Ref. no.: 1217488 Sample no.: 410591-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	123 Colour fastness: 6-7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	193 Colour fastness: 4

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.40 of 2010-12-02.

21 December 2010, Danish Technological Institute, Textile

Charlotte Fischer

Charlotte Fischer
Dirkte tlf.: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

Lea Larsen

Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader



Test Report no. A /412761-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Waterborn	Received: 08-12-2010 Completed: 14-01-2011
Fibre content: 85% polyester/ 15% polyurethane (Manufacturer's information)	Ref. no.: 412761-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	353 Colour fastness: 4-5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	583 Colour fastness: 4-5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	383 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	363 Colour fastness: 4-5

Test Report no. A /412761-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	373 Colour fastness: 4-5

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.41 of 2010-12-23.

14 January 2011, Danish Technological Institute, Textile



Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 415493-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat HoldingA/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Waterborn	Received: 05-01-2011 Completed: 10-02-2011
Fibre content: 85% polyester/ 15% polyurethane (Manufacturer's information)	Ref. no.: 415493-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	673 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	783 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	543 Colour fastness: 3-4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	693 Colour fastness: 4

Test Report no. A 415493-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	343 Colour fastness: 4-5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	193 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	183 Colour fastness: 4

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.41 of 2010-12-23.

10 February 2011, Danish Technological Institute, Textile

Charlotte Fischer

Charlotte Fischer
 Ph. Direct: +45 72 20 21 35
 E-mail: charlotte.fischer@teknologisk.dk

Test responsible

Lea Larsen

Lea Larsen
 Ph. Direct: +45 72 20 21 36
 E-mail: lea.larsen@teknologisk.dk

Co-reader



Test Report no. A 420861-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Waterborn	Received: 14-02-2011 Completed: 07-03-2011
Fibre content: 85% Polyester, 15% Polyurethane (Manufacturer's information)	Sample no.: 420861-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	353 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	373 Colour fastness: 4
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	673 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	383 Colour fastness: 4

Test Report no. A 420861-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	543 Colour fastness: 4

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.42 of 2011-03-01.

7 March 2011, Danish Technological Institute, Textile



Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader