

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: Kvadrat Inc.

December 17, 2020

Subject: Specimens of the submitted sample were prepared and tested in accordance with ASTM E 648-17 and/or Federal Test Method 372. NFPA 253

FLOORING RADIANT PANEL TEST

Sample Description

Kanon col. 0002
Kvadrat Rugs by Kinnasand

Test Assembly

Mounted on 6mm FRC Board
(Using Premium Multi Purpose Adhesive)

<u>Test Results</u>	<u>Specimen No. 1</u>	<u>Specimen No. 2</u>	<u>Specimen No. 3</u>
Critical Radiant Flux	0.54 watts/cm ²	0.48 watts/cm ²	0.51 watts/cm ²
Total Burn Length	37.0 cm	40.0 cm	39.0 cm
Flame Front Out	11.0 minutes	12.0 minutes	11.0 minutes

Average Critical Radiant Flux **0.51 watts/cm²**

Estimated Standard Deviation **0.03 watts/cm²**

5.9% coefficient of variation