

	Page : 1 of 1
	Revision nr. : 4
	Approved by : BV
	<b>Test report Seam Slippage</b> <b>NS-EN 13936-2</b>

Client <b>SAHCO GmbH</b> <b>KREUZBURGER STRASSE 17-19</b> <b>DE-9047 1 NÜRNBERG</b> <b>Tyskland</b>		Product <b>Oaxaca</b>	
Client's reference Sarah Kemmerer		Product specification - tested object	
R-no. <b>R16796</b>		Test completed date 31.10.2020	
Date 03.11.2020	Date of receipt, tested object 27.10.2020	Rev. no. / Rev. date 0/	

MANUFACTURER:

COMPOSITION:

Determination of the seam tension properties according to NS EN ISO 13936-2.  
 Five specimens are taken in each direction.  
 The test specimens are folded and sewn. The specimens are set in a tensile strength tester.  
 A force of 180 N is applied. The gap is measured in mm to nearest 0,5 mm.

	SEAM PARALLELL TO WEFT:	SEAM PARALLELL TO WARP:
Sample no.1:	2,0 mm	2,0 mm
Sample no.2:	2,0 mm	2,0 mm
Sample no.3:	2,0 mm	2,0 mm
Sample no.4:	2,0 mm	2,0 mm
Sample no.5:	2,0 mm	2,0 mm
<b>Average seam gap:</b>	<b>2,0 mm</b>	<b>2,0 mm</b>

<b>Comments:</b>
<b>Deviations from test standards:</b>



Bård Vestre  
 Manager