

# kvadrat

Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltoft Denmark  
T +45 89 53 18 66 F +45 89 53 18 00  
www.kvadrat.dk kvadrat@kvadrat.dk

CVR 45998517 Jyske Bank 5073 117977-1

## Lightfastness ISO 105-B02, method 2

### Vidar 3

Colour	Note
123	5-6
133	5-6
143	5-6
152	5-6
182	6-7
222	6-7
313	6-7
323	6
333	5
353	5-6
363	5-6
443	7
472	6-7
542	7
554	7
582	7
622	5-6
633	5-6
653	7
693	6-7
723	6
733	5-6
743	5-6
772	6-7
872	6-7
913	6
932	5
943	5-6
972	6
1062	5
1511	7
1880	7

DTI A 513873-1, 2013.03.08  
DTI A705813-1, 2016.07.27

Ebeltoft, January 2017 LH/lh

# Test Report

Report No.: A 934284-1



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

**Assignor:** Kvadrat A/S,  
Lundbergsvej 10,  
8400 Ebeltoft

Page 1 of 1  
Chf/leln  
Order no.: 934284  
No. of appendices: 1

**Subject:** Upholstery fabric Vidar 4, 94% new wool, 6% nylon (as per info from the assigner).

**Sampling:** The test material was sampled by the client and received at the Danish Technological Institute 29.06.2020

**Method:** See Appendix 1.

**Period:** The testing was completed 31.07.2020

**Result:** Individual results appear from Appendix 1.

**Storage:** The test material will be destroyed after 6 months, unless otherwise agreed.

**Terms:** The accredited test was carried out according to DANAK's general conditions see [www.danak.dk](http://www.danak.dk) and according to the General Terms and Conditions regarding Commissioned Work Accepted by the Danish Technological Institute, which apply at the time of signing the agreement. The test is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

**Date/place:** 03.08.2020, Danish Technological Institute, Wood and Biomaterials, Textile, Taastrup

*Digitally signed by:*  
Charlotte Fischer  
Ph. Direct: +45 72 20 21 35  
E-mail: chf@teknologisk.dk

*Digitally signed by:*  
Lea Larsen  
Ph. Direct: +45 72 20 21 36  
E-mail: leln@teknologisk.dk

**Signature:** Test responsible

Co-signatory



Report no.: A 964284-1  
 Appendix: 1  
 Page: 1 of 2  
 Initials: Chf/Ieln

<b>Test Methods</b>	<b>Results</b>
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	456 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	386 Colour fastness: 7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	106 Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	146 Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	526 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	786 Colour fastness: 7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	676 Colour fastness: 7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	656 Colour fastness: 6

Report no.: A 964284-1  
 Appendix: 1  
 Page: 2 of 2  
 Initials: Chf/leln

<b>Test Methods</b>	<b>Results</b>
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	956 Colour fastness: 7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	556 Colour fastness: 7