



Report 69626 Test Report

Applicant

Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
DÄNEMARK

Reference

Lone Henriksen

Application

Determination of burning behaviour, smoke emission and dropping behaviour according to ÖNORM A 3800-1.

Test Material

"Basel"

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

Issuing and Signatures

Number of pages contained: 5

Original Issue / Vienna 2012-10-09 / da/KK 1832

Authorised for Institute
Astrid Damböck





Contents

1	Order	2
1.1	Chronology	2
1.2	Samples.....	2
2	Findings / Tests performed.....	3
2.1	Description of the specimen	3
2.2	Test and evaluation of burning behaviour excluding building products	3
2.3	Determination and Classification of dropping behaviour.....	4
2.4	Determination of smoke emission.....	4
3	Remarks	5

1 Order

1.1 Chronology

Date	Received	Order
2012-09-24	2012-09-25	Determination of burning behaviour, smoke emission and dropping behaviour according to ÖNORM A 3800-1.

1.2 Samples

No.	Received	Sample Identification
1	2012-09-24 (1)	"Basel"

(1) Samples provided by the customer. (2) Sample drawn by ÖTI.

2 Findings / Tests performed

2.1 Description of the specimen

Description of the specimen according to DIN 60 000

Test results

Tested sample: 1

Type of fibre according to DIN 60 001 part 1 and DIN ISO 2076	90% Wool 10% Polyamide (declaration by the applicant)
Technological description	woven fabric

2.2 Test and evaluation of burning behaviour excluding building products

Test conditions

Standard: ÖNORM A 3800-1 point 4.1

Arrangement of the sample: fixing of sample with double-sided adhesive tape

Test results

Tested sample: 1

Evaluation criteria	Test		
	1	2	3
Ignition of the not flamed specimen [yes/no]	no	no	no
Afterflame time [min:sec]	0:00	0:00	0:00
Afterglow time [min:sec]	0:00	0:00	0:00
Undestroyed length of flamed specimen [cm]	44	41	42

Classification

According to the classification criteria of ÖNORM A 3800-1, point 4.1, the tested sample

can be classified as "Brennbarkeitsklasse - schwerbrennbar"¹⁾

¹⁾ In the withdrawn standard ÖNORM B 3800-1:1988 classified as "Brennbarkeitsklasse B1-schwerbrennbar"



2.3 Determination and Classification of dropping behaviour

Test Conditions

Standard: ÖNORM A 3800 part 1 item 4.3

Type of specimen: textile fabric

Kind of flaming: Schlyterbrenner

Test Results

Tested sample: 1

	dropping	number of drops falling down	kindling
Test 1	no	0	--
Test 2	yes	2	no
Test 2	yes	2	no

Classification

The tested specimen can be classified according to ÖNORM A 3800-1, item 4.3.1 as:

Tropfenbildungsklasse Tr 1 - nicht tropfend

Note: The determination of the dropping behaviour is done by the "5 drop-rule" according to agreement. In the case of falling down of less than 5 drops there is no risk involved. Therefore the sample is classified as Tropfenbildungsklasse Tr1 – nicht tropfend.

2.4 Determination of smoke emission

Test Conditions

Standard: ÖNORM A 3800 part 1/4.2

Specimen: textile fabric

Arrangement of the specimen: loose

Test results

Tested sample: 1

smoke emission [%]					
Test 1	Test 2	Test 3	Test 4	Test 5	Mean Value
9	11	3	11	3	7

Classification

The tested specimen can be classified according to ÖNORM A 3800-1, item 4.2.1 as:

Qualmbildungsklasse Q1 - schwachqualmend



3 Remarks

Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or the ÖTI.

The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product produced unchanged.

Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

Sample Material

Results of performed tests only refer to the sample material provided.

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

Quality management and accreditations

All tests and services are performed under a quality management system according to EN/IEC ISO 17025.

ÖTI is accredited by several organisations for various tests offered. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/nando/>).

The accreditation by the Federal Ministry of Economy, Family and Youth as testing laboratory was repeated under reference BMWFJ-97.714/0198-I/12/2012 (Individual accredited test procedures are marked with the federal laboratory logo): The accreditation for testing and inspection of construction products was given by the OIB (Austrian Institute of Construction Engineering). Details and other accreditations are given on request and can be found on www.oeti.biz.

Validity type-examination

The validity of the type-examination is generally limited to a maximum of 5 years. If a reference standard will be modified before the 5-year period of validity is expired, the validity remains unchanged, except if the change was made for safety reasons. In this case, the validity ends with the withdrawal of the standard.

If all reference standards remain valid and no changes were made on the prototype, an extension of validity can be done. An application for extension of the validity may be placed at the earliest 12 months and no later than 6 months before the expiry of validity.

This issue replaced for all preceding issues of these type numbers.

Copyright und Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

