

Investigation report

SAHCO GmbH
Fr. Sarah Kemmerer
Kreuzburger Str. 17-19

DE 90471 Nürnberg

contact Alicja Rösler
department Laboratory\Lab-manager
phone +49 (0) 5206/9107 -57
fax +49 (0) 5206/9107 -34
e-mail alicja.roesler@delcotex.de
date 22.12.2020

investigation report No. 20/4237

order description: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

test samples: "art. 600724 Pippa, 10 colorways"

sampling: by the client
orderer: see address
date of order: 07.12.2020
receipt of order: 09.12.2020
date of testing: 21.12.2020

Remark: The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 20/4237

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:


tester Atlas Xenotest alpha LM
light xenon arc beam
filtersystem type 7
sample movement interchangeable barrel
exposure time 166 h - to note 6
test equipment number: PM-Nr. 887001

test results

"art. 600724 Pippa, 10 colorways"

article / colour	Note*
"art 600724 Pippa, color 0750"	3-4
"art 600724 Pippa, color 0550"	4
"art 600724 Pippa, color 0500"	4-5
"art 600724 Pippa, color 0470"	4
"art 600724 Pippa, color 0380"	3-4
"art 600724 Pippa, color 0250"	4
"art 600724 Pippa, color 0210"	5
"art 600724 Pippa, color 0190"	4
"art 600724 Pippa, color 0140"	5
"art 600724 Pippa, color 0110"	5-6

* The results based on using the blue scale. Note 1 = intense colour change, Note 8 = no colour change



i.A. Alicja Rösler

Laboratory/Lab-manager

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.

Investigation report No. 20/4237

Attachment

article: "art. 600724 Pippa"

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

col.: 0750

col.: 0550

col.: 0500

col.: 0470



col.: 0380

col.: 0250

col.: 0210

col.: 0190



Investigation report No. 20/4237

Attachment

article: "art. 600724 Pippa"

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

col.: 0140

col.. 0110

