



*Perrini is a trading name of Textiles F.R. Ltd.*

Unit 4B, (30) Wharfedale Road  
Euroway Trading Estate  
Bradford  
West Yorkshire  
BD4 6SG

**Textiles F.R. Limited**  
*Flame Retardancy Finishers & Consultants*

Tel: 01274 651230  
Fax: 01274 651305  
E-mail: sales@textilesfr.co.uk  
Web site: www.textilesfr.co.uk



**Test Report & Certificate**

UKAS TESTING LABORATORY No. 1413

British Standard Flammability Test	Test Document	<b>31522</b>	Page 1 of 2
BS5867-2:2008:Type B			
Customer Account SAH003	Order Details		
SAHCO GMBH	TFR Order No	302490	
KREUZBURGER STRASSE 17-19	Customer Order	SK	
90471 NUREMBERG	Order Date	15/09/2020	
GERMANY	Fabric Description	600691 SEERSUCKER	
	Fabric Composition	5% POLY:95% TREVIRA CS	
	Quantity (metres)	1.0	

Fabric Treatment      Sample tested in an 'as received' state.

Cleansing              Flammability testing was performed without the durability requirements stated in section 5 of BS5867-2:2008 being completed.

Filling                    Not applicable.

Conditioning            Test specimens were conditioned in an atmosphere having a temperature of 20±2°C and relative humidity 65±5% for a minimum of 24 hours prior to testing.

Test Enclosure Conditions	Temperature	Humidity
	20 °C	65 %

Procedure                Six specimens were prepared each measuring 200± 2mm x 160± 2mm, three with the longer dimension in the length, and three with the longer dimension in the width. A butane flame was applied to each sample face for 15 seconds.

Compliance Requirements      No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen, and there shall be no separation of flaming debris from any specimen.

Disclaimer                This test was carried out in accordance with BS EN ISO 15025 : 2002 Procedure A. The results may not apply to situations where there is a restricted air supply or prolonged exposure to large sources of heat such as in a conflagration.

Decision Rule            Textiles FR Ltd will use a Binary Decision Rule incorporating a guard band.  
Where statements of conformity are made in this report, the following decision rules are applied;  
Pass - Results +/- expanded uncertainty within limits / specifications.  
Fail - Results +/- expanded uncertainty exceeds limits / specifications.

Result                    **PASS**      Specimen complied to the requirements for BS5867-2:2008:Type B. Flammability testing was performed without the durability requirements stated in section 5 of BS5867-2:2008 being completed.



*Perovits is a trading name of Textiles F.R. Ltd.*

Unit 4B, (30) Wharfedale Road  
Euroway Trading Estate  
Bradford  
West Yorkshire  
BD4 6SG

**Textiles F.R. Limited**  
*Flame Retardancy Finishers & Consultants*

Tel: 01274 651230  
Fax: 01274 651305  
E-mail: sales@textilesfr.co.uk  
Web site: www.textilesfr.co.uk



**British Standard Flammability Test**

BS5867-2:2008:Type B

Customer Account SAH003

SAHCO GMBH

KREUZBURGER STRASSE 17-19

90471 NUREMBERG

GERMANY

Test Document **31522**

Page 2 of 2

CUD Contract Curtain Test

Order Details

TFR Order No 302490

Customer Order SK

Order Date 15/09/2020

Fabric Description 600691 SEERSUCKER

Fabric Composition 5% POLY:95% TREVIRA CS

Quantity (metres) 1.0

Warp and Weft Observations

	Rep 1	Rep 2	Rep 3		Rep 1	Rep 2	Rep 3
Warp Flame to Edge	No	No	No	Weft Flame to Edge	No	No	No
Warp Hole to Edge	No	No	No	Weft Hole to Edge	No	No	No
Warp Flaming Debris	No	No	No	Weft Flaming Debris	No	No	No

Authorised by Kim Button  
Director

Test Conducted by Ray Berry  
Laboratory Technician