

## EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kinnasand / Kvadrat

Date: 17/05/2021

Fabric details Type: Raffia  
Colour: 14 & 33  
Order:  
Item number 70840001  
Manufacturer: Kinnasand / Kvadrat

Specimen Diameter: 100 mm  
Thickness: 0.35 mm  
Area specific mass: 146 g/m<sup>2</sup>

$u_l$ (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	28
14.16	30
11.80	32
9.44	34
7.12	36
4.72	34



**Airflow Resistance**

**$R_s = 39$  Pa s/m**