


EN 29053 - Determination of airflow resistance

Direct airflow method - method A

Client: Kinnasand / Kvadrat
Date: 30/04/2021
Fabric details: Type: Touch Point
Colour: 5&11
Order:
Item number: 70870001
Manufacturer: Kinnasand / Kvadrat

Specimen: Diameter: 100 mm
Thickness: 0.78 mm
Area specific mass: 321 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	118
14.16	121
11.80	124
9.44	127
7.12	129
4.72	129



Airflow Resistance

$R_s = 135$ Pa s/m