

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kinnasand / Kvadrat

Date: 28/04/2021

Fabric details Type: Cheno
Colour: 6&26
Order:
Item number 70850001
Manufacturer: Kinnasand / Kvadrat

Specimen Diameter: 100 mm
Thickness: 1.8 mm
Area specific mass: 346 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	41
14.16	43
11.80	47
9.44	48
7.12	49
4.72	50



Airflow Resistance

$R_s = 55$ Pa s/m