

## EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kinnasand / Kvadrat

Date: 30/04/2021

Fabric details Type: Shift  
Colour: 13&33  
Order:  
Item number 70940001  
Manufacturer: Kinnasand / Kvadrat

Specimen Diameter: 100 mm  
Thickness: 0.7 mm  
Area specific mass: 236 g/m<sup>2</sup>

$u_l$ (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	59
14.16	63
11.80	64
9.44	68
7.12	69
4.72	71



**Airflow Resistance**

**$R_s = 76$  Pa s/m**