


EN 29053 - Determination of airflow resistance

Direct airflow method - method A

Client: Kinnasand / Kvadrat
Date: 30/04/2021
Fabric details: Type: Pleats
Colour: 3&14
Order:
Item number: 70900001
Manufacturer: Kinnasand / Kvadrat

Specimen: Diameter: 100 mm
Thickness: 0.8 mm
Area specific mass: 201 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	344
14.16	346
11.80	349
9.44	353
7.12	353
4.72	363



Airflow Resistance

$R_s = 367$ Pa s/m