

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kinnasand / Kvadrat

Date: 28/04/2021

Fabric details Type: Highlight
Colour: 7&24
Order:
Item number -
Manufacturer: Kinnasand / Kvadrat

Specimen Diameter: 100 mm
Thickness: 0.78 mm
Area specific mass: 379 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	2052
14.16	2054
11.80	2054
9.44	2059
7.12	2054
4.72	2074



Airflow Resistance

$R_s = 2073$ Pa s/m