

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kinnasand / Kvadrat

Date: 19/05/2021

Fabric details Type: Artic
Colour: 3&13
Order:
Item number 70950001
Manufacturer: Kinnasand / Kvadrat

Specimen Diameter: 100 mm
Thickness: 1.26 mm
Area specific mass: 470 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	60
14.16	62
11.80	65
9.44	67
7.12	71
4.72	74



Airflow Resistance

$R_s = 79$ Pa s/m