

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kinnasand / Kvadrat

Date: 28/04/2021

Fabric details Type: Allround
Colour: 13&16
Order:
Item number 71010001
Manufacturer: Kinnasand / Kvadrat

Specimen Diameter: 100 mm
Thickness: 0.41 mm
Area specific mass: 141 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	99
14.16	102
11.80	106
9.44	110
7.12	111
4.72	113



Airflow Resistance

$R_s = 119$ Pa s/m