### **Test Report**

Report Number: 977379-4-TEX

Assignor:



#### DANISH TECHNOLOGICAL

**INSTITUTE** 

Gregersensvej 1 DK-2630 Taastrup +45 72 20 20 00 info@teknologisk.dk www.teknologisk.dk

Page 1 of 5 Init.: CHF/LELN Order no.: 977379

Encl.: 0

Kinnasand GmbH, Danziger Strasse 6, D-26655 Westerstede, Germany

Material: Sample of fabric designated: Touch Point 7087. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the

assignor and received at Danish Technological Institute on 28 April 2021.

**Period:** The test took place from 29 April 2021 to 26 May 2021.

**Method:** The test methods used are referenced in connection with the results. See page 5.

**Test results:** The results are shown on page 5.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC

17025:2017) and in accordance with the General Terms and Conditions of Danish

Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Building and Construction

Signature: This document is only valid with a digital signature from Danish Technological Institute. The

date of issue appears from the digital signature.

Charlotte Fischer Senior Consultant









# Samples

Sample mark	Description	Photo
Col. 0012	Sample of fabric Designated: Touch Point 7087 color. 0012	
Col. 0023	Sample of fabric Designated: Touch Point 7087 color. 0023	
Col. 0033	Sample of fabric Designated: Touch Point 7087 color. 0033	
Col. 0014	Sample of fabric Designated: Touch Point 7087 color. 0014	
Col. 0006	Sample of fabric Designated: Touch Point 7087 color. 0006	

977379-4-TEX Page 2 of 5



# Samples (continued)

Sample mark	Description	Photo
Col. 0002	Sample of fabric Designated: Touch Point 7087 color. 0002	
Col. 0024	Sample of fabric Designated: Touch Point 7087 color. 0024	
Col. 0005	Sample of fabric Designated: Touch Point 7087 color. 0005	
Col. 0015	Sample of fabric Designated: Touch Point 7087 color. 0015	
Col. 0011	Sample of fabric Designated: Touch Point 7087 color. 0011	

977379-4-TEX Page 3 of 5



# Samples (continued)

Sample mark	Description	Photo
Col. 0001	Sample of fabric Designated: Touch Point 7087 color. 0001	
Col. 0013	Sample of fabric Designated: Touch Point 7087 color. 0013	

977379-4-TEX Page 4 of 5



#### Results

#### Test of Sample of fabric designated: Touch Point 7087

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
Col. 0012	5-6
Col. 0023	5
Col. 0033	4-5
Col. 0014	4
Col. 0006	5
Col. 0002	7
Col. 0024	5
Col. 0005	5
Col. 0015	5
Col. 0011	6
Col. 0001	5
Col. 0013	5-6

977379-4-TEX Page 5 of 5