

Test Report

Report Number:
977379-10-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 3
Init.: CHF/LELN
Order no.: 977379
Encl.: 0

Assignor: Kinnasand GmbH, Danziger Strasse 6 , D-26655 Westerstede, Germany

Material: Sample of fabric designated: Ripple 7102. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 28 April 2021.

Period: The test took place from 29 April 2021 to 26 May 2021.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown on page 3.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Building and Construction

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

27 May 2021

DANISH TECHNOLOGICAL INSTITUTE









DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
Col. 0002	Sample of fabric Designated: Ripple 7102 Color. 0002	
Col. 0016	Sample of fabric Designated: Ripple 7102 Color. 0016	
Col. 0033	Sample of fabric Designated: Ripple 7102 Color. 0033	
Col. 0012	Sample of fabric Designated: Ripple 7102 Color. 0012	
Col. 0013	Sample of fabric Designated: Ripple 7102 Color. 0013	
Col. 0001	Sample of fabric Designated: Ripple 7102 Color. 0001	



Results

Test of Sample of fabric designated: Ripple 7102

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
Col. 0002	7
Col. 0016	3
Col. 0033	7
Col. 0012	6
Col. 0013	6
Col. 0001	7
