

# EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client: Kinnasand

Date: 12-12-19

Type: Estate 47% linen 45% polyacrylic  
Colour: 14 8% polyester  
Order:  
Batch:  
Manufacturer: Kinnasand

Specimen Diameter: 100 mm  
Thickness: 1.57 mm  
Area specific mass: 622 g/m<sup>2</sup>

$u_l$ (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	212
14.16	214
11.80	214
9.44	216
7.12	218
4.42	231



**Airflow Resistance**

**$R_s = 230$  Pa s/m**