

# EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client: Kinnasand

Date: 12-12-19

Type: Fields 100% Trevira CS  
Colour: 25  
Order:  
Batch:  
Manufacturer: Kinnasand

Specimen Diameter: 100 mm  
Thickness: 0.25 mm  
Area specific mass: 68 g/m<sup>2</sup>

$u_l$ (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	6
14.16	7
11.80	10
9.44	10
7.12	11
4.42	14



**Airflow Resistance**

**$R_s = 16$  Pa s/m**